

**ACRYLIC PRIMER** – One-component, filling acrylic primer intended for levelling surfaces coated with putty and old paint coatings. Perfect for spot repairs. Very short drying time allowing for making quick repairs is the main advantage of the primer. VOC II/B/e limit = 840g/l VOC < 720 g/l.

SHELF LIFE 5years/20°C


| Vol. (ml) | Name           | Article no. | Colour | units/pack. |
|-----------|----------------|-------------|--------|-------------|
| 500       | Acrylic primer | 34402       | Grey   | 6           |
|           |                | 34412       | Black  | 6           |



Shake for 2 min.



Apply 2-3 coats



5-10 min.



15-30 min./20°C  
15 min./60°C



P360-500



P800-1000



Clean the valve for 5 s

**WHEEL SPRAY** – Fast-drying spray coat, intended mainly for renovation and repair of rims and caps made of steel and aluminium. Has very good coating, durable gloss, resistance to water, petrol and atmospheric conditions. VOC II/B/e limit = 840g/l VOC < 690 g/l.

SHELF LIFE 5years/20°C


| Vol. (ml) | Name        | Article no. | Colour     | units/pack. |
|-----------|-------------|-------------|------------|-------------|
| 500       | Wheel spray | 34102       | Silver     | 6           |
|           |             | 34112       | Steelwheel | 6           |
|           |             | 34122       | Matt black | 6           |
|           |             | 34132       | Black      | 6           |



Shake for 2 min.



Apply 2-4 coats



5-10min.



2 h/20°C



Clean the valve for 5 s


**CLEARCOAT** – One-component, thermoplastic product with very good levelling and easy to polish. Perfect for spot repairs. Available in Glossy and Matt versions. VOC II/B/e limit = 840g/l VOC < 670 g/l

SHELF LIFE 5years/20°C


| Vol. (ml) | Name      | Article no. | Colour          | units/pack. |
|-----------|-----------|-------------|-----------------|-------------|
| 500       | Clearcoat | 34002       | Colourless      | 6           |
|           |           | 90406       | Colourless Matt | 6           |




Shake for 2 min.



Apply 2-3 coats



5-10min.



2 h/20°C



Clean the valve for 5 s

**ANTIGRAVEL HS** – The product forms a durable, very flexible and coarse-grained layer that is resistant to the impact of stones. Protects against petrol, oil, water and salt. It also has sound-absorbing and sound-proofing properties. The product is based on synthetic resins; it does not contain asphalt or bitumen and can be coated with any clear coats. Ecological product with reduced solvent content. VOC II/B/e limit = 840g/l VOC < 590 g/l  
SHELF LIFE 5years/20°C

| Vol.<br>(ml) | Name          | Article no. | Colour | units/pack. |
|--------------|---------------|-------------|--------|-------------|
| 500          | Antigravel HS | 34252       | Black  | 6           |



Degrease




Sand-paper




Degrease




Shake for 2 min.



Apply 2-3 coats



5-10 min.



40-60 min./20°C



Clean the valve  
for 5 s

**ANTIGRAVEL MS** – The product forms a durable, very flexible and fine-grained layer that is resistant to the impact of stones. Protects against petrol, oil, water and salt. It also has sound-absorbing and sound-proofing properties. The product is based on synthetic resins; it does not contain asphalt or bitumen and can be coated with any clear coats. VOC II/B/e limit = 840g/l VOC < 580 g/l.  
SHELF LIFE 5years/20°C

| Vol.<br>(ml) | Name          | Article no. | Colour | units/pack. |
|--------------|---------------|-------------|--------|-------------|
| 500          | Antigravel MS | 34202       | Black  | 6           |
|              |               | 34212       | Grey   | 6           |
|              |               | 34222       | White  | 6           |



Degrease




Sand-paper




Degrease




Shake for 2 min.



Apply 2-3 coats



5-10 min.



40-60 min./20°C




Clean the valve  
for 5 s

**CAVITY WAX** – Perfect protection against corrosion. Resistant to atmospheric factors and to weak acids and bases. It has good penetration; penetrating deep inside slots forms a flexible and tight coating protecting against water and salt. It has a very good ability to displace humidity from the substrate. VOC II/B/e limit = 840g/l VOC < 570 g/l.  
SHELF LIFE 5years/20°C

| Vol.<br>(ml) | Name       | Article no. | Colour | units/pack. |
|--------------|------------|-------------|--------|-------------|
| 500          | Cavity wax | 34012       | Clear  | 6           |



Shake for 2 min.



Apply the product into slots with the  
adapter



Clean the valve for 5 s

**CONTROL SPRAY** – A product designed to help control the sanding process of surfaces on which polyester putty or primer was applied. It is used to detect sanding scratches and unevenness. The application of a thin non-homogeneous layer helps easily detect the areas and extent for required further processing.

Extremely short drying time lets you almost instantly commence sanding work.


VOC II/B/e limit = 840g/l VOC < 740 g/l

SHELF LIFE 5years/20°C


| Vol. (ml) | Name          | Article no. | Colour | units/pack. |
|-----------|---------------|-------------|--------|-------------|
| 500       | Control spray | 34022       | Black  | 6           |



Shake for 2 min.



Spray 1 coat



Leave for 3-5 min.



Sand-paper



Clean the valve for 5 s

**STRUCTURE TOPCOAT** – Fast-drying decorative acrylic coat with very good covering properties, with a fine-grained texture which imitates plastic. VOC II/B/e limit = 840g/l VOC < 680 g/l

SHELF LIFE 5years/20°C


| Vol. (ml) | Name              | Article no. | Colour     | units/pack. |
|-----------|-------------------|-------------|------------|-------------|
| 500       | Structure topcoat | 34502       | Black      | 6           |
|           |                   | 34512       | Anthracite | 6           |




Degrease




Shake for 2 min.



Apply 1-2 coats



5-10 min.



2 h/20 °C



Clean the valve for 5 s

**PLASTIC PRIMER** – Fast-drying, colourless primer that increases the adhesion of acrylic primers, acrylic and polyurethane coats for different substrate types (steel, galvanised steel, aluminium), especially plastic (including polypropylene and its mixtures). VOC II/B/e limit = 840g/l VOC < 710 g/l

SHELF LIFE 5years/20°C

| Vol. (ml) | Name           | Article no. | Colour    | units/pack. |
|-----------|----------------|-------------|-----------|-------------|
| 500       | Plastic primer | 34482       | Yellowish | 6           |



Degrease




Sand-paper




Degrease




Shake for 2 min.



Apply 1-2 coats



5-10 min.



15 min./20 °C




Clean the valve for 5 s

**ACRYLIC TOPCOAT** – Fast-drying thermoplastic acryl topcoat with very good covering properties. VOC II/B/e limit = 840g/l VOC < 715 g/l.  
SHELF LIFE 5years/20°C


| Vol.<br>(ml) | Name            | Article no. | Colour       | units/pack. |
|--------------|-----------------|-------------|--------------|-------------|
| 500          | Acrylic topcoat | 34312       | Glossy white | 6           |
|              |                 | 34302       | Glossy black | 6           |
|              |                 | 34342       | Satin black  | 6           |
|              |                 | 34352       | Matt black   | 6           |




Shake for 2 min.



Apply 2-3 coats



5-10 min.



2 h/20 °C

## PAINT REMOVER

The product is intended for removing the majority of paint types and other coatings from various surfaces (e.g. metal, stone, wood, glass, asphalt or concrete). It acts by effectively and quickly penetrating the coating and weakening its bonding to the substrate to enable easy removal.


The product has a gel consistency. Approximate yield: 0.8 m<sup>2</sup>. Test the resistance of the substrate to damage from the product before use. The spray must have an ambient temperature and the substrate temperature should be from +5 to +30°C. Shake before application. The peak effectiveness and removal time ranges from 20 to 30 minutes, depending on the quality, type and age of the coating being removed. The process may require repeating in certain conditions. Remove the softened coating with suitable tools. The removed paint coating should be treated as chemical waste.  
VOC II/B/a limit = 850 g/l VOC < 809 g/l.

SHELF LIFE 2years/20°C

| Capacity<br>(ml) | Name          | Part no. | Colour | Pcs./pack |
|------------------|---------------|----------|--------|-----------|
| 400              | Paint remover | 91208    | Clear  | 6         |




Shake for  
2 min



Apply  
for 5 s



Clean the valve



Wait from  
20 to 30 min



Strip the coating

**BITUMEN UNDERBODY COATING** – forms a flexible coat that resists weather, weak acids and alkalis, as well as stone chip damage. The coat displays sound-proofing and sound-dampening properties. The product is a one-component formula that dries fast and exhibits good hiding power.

VOC II/B/e limit = 840g/l VOC < 550 g/l.

SHELF LIFE 5years/20°C


| Capacity (ml) | Name                      | Part no. | Colour | Pcs. per pack |
|---------------|---------------------------|----------|--------|---------------|
| 500           | Bitumen Underbody Coating | 90397    | black  | 6             |




Degrease




Shake for 2 min



Apply in 3-4 layers



5-10 min



60 min/20°C



Purge the valve for 5 s

**ALU-ZINC** – a fast drying product with excellent hiding power which provides anti-corrosion protection and adheres extremely well to steel and galvanized steel. The resulting coat has good resistance to weather and petrol. The coated surfaces can be fusion welded. Maximum temperature resistance: 250°C.


VOC II/B/a limit = 850 g/l VOC < 690 g/l.

SHELF LIFE 5years/20°C


| Capacity (ml) | Name       | Part no. | Colour | Pcs. per pack |
|---------------|------------|----------|--------|---------------|
| 400           | Alu - Zinc | 90408    | silver | 6             |




Shake for 2 min



Apply in 2-3 layers



5-10 min



2 h/20°C



Purge the valve for 5 s

**ZINC** – A fast-drying product with good hiding power, excellent anti-corrosive properties and extremely good adhesion to steel and galvanized steel. The resulting coat resists weather and petrol. The coated surfaces can be fusion welded. Maximum temperature resistance: 350°C.


VOC II/B/a limit = 850 g/l VOC < 650 g/l.

SHELF LIFE 5years/20°C


| Capacity (ml) | Name | Part no. | Colour | Pcs. per pack |
|---------------|------|----------|--------|---------------|
| 400           | Zinc | 90407    | silver | 6             |




Shake for 2 min



Apply in 2-3 layers



5-10 min



2 h/20°C



Purge the valve for 5 s

**EPOXY PRIMER** – a thin-coat anti-corrosive epoxy primer spray for spot repairs. Available in grey. Equipped a spot-applicator nozzle.

VOC II/B/a limit = 850 g/l VOC < 690 g/l

SHELF LIFE 5years/20°C


| Capacity (ml) | Name         | Part no. | Colour | Pcs. per pack |
|---------------|--------------|----------|--------|---------------|
| 500           | Epoxy Primer | 91141    | Grey   | 6             |




Shake for 2 min



Apply in 2-3 layers



5 min



10 – 15  
min/20°C



Purge the valve  
for 5 s

### Other informations:

Registration number 000024104

The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.